



ACADIAN INDUSTRIAL TEXTILES
WOVEN POLYPROPYLENE CONTAINMENT FABRIC
STYLE 11285

June 20, 2006

Specifications

FIBER CONTENT	100% Polypropylene
COLOR	Black
WEIGHT ASTM D-5261	4.7 oz/sq. yd.
TENSILE STRENGTH ASTM D-4632, Grab Method	Warp: 251 lbs Fill: 250 lbs
ELONGATION ASTM D-4632, Grab Method	Warp: 17% Fill: 17 %
PUNCTURE STRENGTH ASTM D-4833 Modified	133.8 lbs
TEAR STRENGTH ASTM D-4533, Trap Method	Warp: 105 lbs Fill: 95 lbs
BURST STRENGTH ASTM D-3786	414 psi
CONSTRUCTION	20 X 20
AIR FLOW RATE ASTM D-737	627 ft ³ per minute per ft ²
SHADE FACTOR	85%

NOTE: Solid yellow stripes to be woven 11.5 inches from both sides of selvage plus a center line 62" from selvage.

The information presented herein, while not guaranteed, is to the best of our knowledge, true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee, expressed or implied, is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.

TECHNICAL DATA PROVIDED BY SGI TESTING