



ACADIAN INDUSTRIAL TEXTILES
WOVEN POLYPROPYLENE CONTAINMENT FABRIC
STYLE: 11285

V117

Specifications

FIBER CONTENT	100% Polypropylene
COLOR	Black
CONSTRUCTION	20 x 20
SHADE FACTOR	85 %
WEIGHT ASTM D-5261	4.7 oz./yd ²
TENSILE STRENGTH ASTM D-4632, Grab Method	Warp: 251 lbs. Fill: 250 lbs.
ELONGATION ASTM D-4632, Grab Method	Warp: 17% Fill: 17 %
PUNCTURE STRENGTH ASTM D-4833 Modified	133.8 lbs.
TEAR STRENGTH ASTM D-4533, Trap Method	Warp: 105 lbs. Fill: 95 lbs.
BURST STRENGTH ASTM D-3786	414 psi
AIR FLOW RATE ASTM D-737	309 ft ³ per minute per ft ²
PORE SIZE	0.018" X 0.018"

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. Product specifications are typical average values and are subject to change.

TECHNICAL DATA SUPPLIED BY PRODUCING MILL AND SGI TESTING