



WOVEN POLYPROPYLENE TRUCK COVER FABRIC SPECIFICATIONS

Style #	10434	10434-TR	10446-TC
FIBER CONTENT	Polypropylene	Polypropylene	Polypropylene
FINISH	N/A	Calendered	Calendered
CONSTRUCTION	53 x 48	55 x 48	30 x 20
WEIGHT (ASTM D-3776)	7.8 oz/yd ²	7.8 oz/yd ²	6.4 oz/yd ²
THICKNESS	31 MIL	20 MIL	14 MIL
TENSILE STRENGTH (ASTM D-4632, Grab Method)	Warp: 465 lbs Fill: 400 lbs	Warp: 465 lbs Fill: 400 lbs	Warp: 525 lbs Fill: 290 lbs
TRAPEZOIDAL TEAR STRENGTH (ASTM D-4553)	Warp: 224.5 lbf Fill: 174.5 lbf	Warp: 185 lbf Fill: 165 lbf	Warp: 150 lbf Fill: 65 lbf
BURST STRENGTH (ASTM D-3787)	777.8 psi	929 psi	784 psi
AIR PERMEABILITY (ASTM D-737)	182 cm ³ /sec/cm ²	144.2 cm ³ /sec/cm ²	79.9 cm ³ /sec/cm ²

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Product specifications contain typical average values achieved through testing in controlled conditions and are subject to updating at the sole discretion of Acadian Inc. Buyer is responsible for verifying the suitability of product for a particular use. In no event will Acadian Inc.'s liability exceed the purchase value of the product nor will Acadian Inc. be liable for loss of profit or special, indirect or consequential damages.

UV INHIBITOR: CARBON BLACK

TECHNICAL DATA PROVIDED BY PRODUCING MILL AND VERIFIED THROUGH 3rd PARTY TESTING