



RAIN PROTECTION FABRIC SPECIFICATIONS

Style #	10394
FIBER CONTENT	Polypropylene
COLOR	White
CONSTRUCTION	11 x 11
WEIGHT (ASTM D-3776)	3.0 oz/yd ²
TENSILE STRENGTH (ASTM D-4632, Grab Method)	Warp: 251 lbs Fill: 217 lbs
ELONGATION (ASTM D-4632, Grab Method)	Warp: 14% Fill: 12%
BURST STRENGTH (ASTM D-6241)	627 psi
TRAPEZOIDAL TEAR STRENGTH (ASTM D-4553)	Warp: 92 lbf Fill: 92 lbf
<p>The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Product specifications contain typical average values achieved through testing in controlled conditions and are subject to updating at the sole discretion of Acadian Inc. Buyer is responsible for verifying the suitability of product for a particular use. In no event will Acadian Inc.'s liability exceed the purchase value of the product nor will Acadian Inc. be liable for loss of profit or special, indirect or consequential damages.</p>	

U.V. INHIBITOR: HALS
TECHNICAL DATA PROVIDED BY PRODUCING MILL